


PB28 COBALT ALUMINATE BLUE SPINEL

MAIN CHARACTERISTICS

- CoAl_2O_4
- Pigment Blue 28 (C.I. 77346)
- Spinel structure
- Reddish blue shade
- Ease of dispersion
- UV transparent, opaque to visible light, with moderate NIR reflectance ("cool" pigment)



Heat fastness	>500°C*, 5 min
Light fastness	Excellent (8 on blue wool scale)
Weather fastness	Excellent (5 on grey scale)
Acid fastness	Excellent
Alkali fastness	Excellent
Cement compatibility	Excellent
Solvent fastness	Excellent



RECOMMENDED PRODUCTS

22-5091	Standard grade	22-5600	Turquoise Blue, high tinting strength
10336	High tinting strength, reddish shade	22-5700	Turquoise Blue, greenish shade
10446	High tinting strength, reddish shade	22-5475	Modified cobalt blue with most reddish shade in the range
22-5500	Turquoise Blue		

* Paint