

PBk26 MANGANESE FERRITE BLACK SPINEL

MAIN CHARACTERISTICS

- MnFe_2O_4
- Pigment Black 26 (C.I. 77494)
- Spinel structure
- Very bluish/deep shade, the strongest black CICP
- Ease of dispersion
- Opaque to visible light, UV/NIR absorbent
- The black CICP with the highest heat fastness, very suitable for high temperature resistant coatings

Heat fastness	>500°C*, 5 min
Light fastness	Excellent (8 on blue wool scale)
Weather fastness	Excellent (5 on grey scale)
Acid fastness	Excellent
Alkali fastness	Excellent
Cement compatibility	Excellent
Solvent fastness	Excellent



RECOMMENDED PRODUCTS

24-3060 High tinting strength, very bluish shade

* Paint