# PY164 MANGANESE ANTIMONY TITANIUM BUFF RUTILE

## MAIN CHARACTERISTICS

- (Ti,Mn,Sb) $O_2$
- Pigment Yellow 164 ( C.I. 77899)
- Dark brown shade
- Ease of dispersion
- Opaque to visible light, with high NIR reflectance (“cool” pigment)

| | |
|---|---|
| **Heat fastness** | 200°C, 30 min |
| **Light fastness** | Excellent (8 on blue wool scale) |
| **Weather fastness** | Excellen (5 on grey scale) |
| **Acid fastness** | Excellent |
| **Alkali fastness** | Excellent |
| **Cement compatibility** | Excellent |
| **Solvent fastness** | Excellent |

## RECOMMENDED PRODUCTS

**10550** Standard grade